In situ thermal decomposition route: Preparation and characterization of nano nickel, cobalt, and copper oxides using an aromatic amine complexes as a low-cost simple precursor

Moamen S. Refat^{1*}, Soha F. Mohamed², Tariq A. Altalhi¹, Safyah B. Bakare³ and Ghaferah H. Al-Hazmi⁴

¹Department of Chemistry, College of Science, Taif University, P.O. Box 11099, Taif 21944, Saudi Arabia

²Department of Chemistry, College of Science, Zagazig University, Zagazig, Egypt

³Faculty of Education, Shaqra University, Al Muzahimiyah, Shaqra, Riyadh Province, P.O. Box 205, Zip Code 11972, Kingdom Saudi Arabia

⁴Department of Chemistry, College of Science, Princess Nourah bint Abdulrahman University, Riyadh 11671, KSA

*Corresponding author: e-mail: msrefat@yahoo.com & moamen@tu.edu.sa

The main interest now is the development of metallic or inorganic-organic compounds to prepare nanoparticle materials. The use of new compounds could be beneficial and open a new method for preparing nanomaterials to control the size, shape, and size of the nanocrystals. In this article, the thermal decomposition of $[M_2(o\text{-tol})_2(H_2O)_8]Cl_4$ (where o-tol is *ortho*-tolidine compound, $M = Ni^{2+}, Co^{2+}, Cu^{2+}$) new precursor complex was discussed in solid-state conditions. The thermal decomposition route showed that the synthesized three complexes were easily decomposed into NiO, Co_3O_4 and CuO nanoparticles. This decomposition was performed at low temperatures ($\sim 600^\circ C$) in atmospheric air without using any expensive and toxic solvent or complicated equipment. The obtained product was identified by Fourier transform infrared spectroscopy (FT-IR), X-ray diffraction (XRD), transmission electron microscopy (TEM) and energy-dispersive X-ray spectroscopy (EDX). FT-IR, XRD and EDX analyses revealed that the NiO nanoparticles exhibit a face-centered-cubic lattice structure with a crystallite size of 9–12 nm. The formation of a highly pure spinel-type Co_3O_4 phase with cubic structure showed that the Co_3O_4 nanoparticles have a sphere-like morphology with an average size of 8–10 nm. The XRD patterns of the CuO confirmed that the monoclinic phase with the average diameter of the spherical nanoparticles was approximately 9–15 nm.

Keywords: o-tolidine; NiO, Co_3O_4 , CuO, XRD, TEM, nanoparticles; complexation.

INTRODUCTION

Ortho-tolidine is an organic compound with the molecular formula $(CH_3-C_6H_4-NH_2)_2$. It is a colorless organic compound, slightly soluble in water, forms salts with acids, used mainly for dye production¹, as intermediate to produce soluble azo dyes and insoluble textile pigments, leather, paper industries, and to produce certain elastomers. o-Tolidine was widely used as a reagent/indicator in analytical, clinical, and forensic chemistry, such as in the analytical determination of gold, or determination of the chlorine level in swimming pool water².

Transition metal oxide nanoparticles represent an important class of inorganic nanomaterials that have been investigated extensively due to their interesting catalytic, electronic, and magnetic properties relative to those of the bulk counterparts, and the wide scope of their potential applications³. The nickel oxide nanoparticles (NiO) are one of the supreme transition metal oxides, it has been a p-type semiconductor behavior. The different features of the NiO nanoparticles have prompted different research topics. The quantum size, high specific surface area, volume, and macroscopic quantum tunneling effects revealed the unique magnetic, electronic, catalytic, chemical, and optical properties of the NiO nanoparticles. These properties encouraged their extensive application in ultra-magnetic devices, photoelectric smart windows, photocatalytic applications, electrochemical supercapacitors, photoelectric devices, and gas sensors^{4–9}. NiO nanoparticles are also magnetic nanoparticles with good electrochemical activity, which motivate their use in electrochemical biosensors^{8,9}. Cobalt oxide (Co_3O_4) with spinel-type as a semiconductor material having realizable applications in gas sensors¹⁰, heterogeneous catalysts¹¹, electrochemical devices¹², lithium-ion

batteries¹³, materials magnetism^{14,15} and photocatalysts¹⁶. In literature, increasing interest has been focused on the synthesis of Co_3O_4 nanostructures due to the influence of particle size on their properties and applications¹⁷. Various wet chemical methods such as hydrothermal/thermal solvent method¹⁸, combustion method¹⁹, microwave heating²⁰, gel solution process²¹, spray pyrolysis²², sonochemical method²³, co-sedimentation²⁴, ionic liquid-assisted method²⁵, a polyol method²⁶ and a non-aqueous method²⁷ are reported for the assembly of Co_3O_4 nanostructures. However, most of these methods involve complex processes, high sintering temperatures, and expensive and toxic precursors. Additionally, they are either time-consuming or require expensive tools. Solid-state thermolysis of molecular precursors is the simplest and least expensive to preparing metal oxide nanostructures. This promising technology offers many unique advantages and significant advantages over other methods including easy work, relatively short reaction time, and preparation of numerous inorganic nanomaterials with unique sizes, specific shapes, and narrow size distribution²⁸. The copper oxide (CuO) has been studied as a p-type semiconductor material with a narrow band gap of 1.2 eV, because of its natural abundance of raw materials, low-cost production processing, non-toxic nature, and reasonably good electrical and optical properties. CuO nanoparticles have been of great interest due to their potential applications in a wide range of fields including electronic and optoelectronic devices, such as microelectromechanical systems, field-effect transistors, electrochemical cells, gas sensors, magnetic storage media, solar cells, and field emitters, and nanocatalysis devices. It has also been emphasized recently that regardless of size, the shape of the nanostructure is equally important

for controlling various properties²⁹. The main task of this work is to synthesis nanoparticles of NiO, Co₃O₄, and CuO using the thermal decomposition method and its physicochemical characterizations.

This article is aimed to synthesis of three transition metal oxide nanoparticles from a simple precursor in a short time and with an easy, low temperature, low-cost method without using any special instrument. To the best of our knowledge, this is the first report on the synthesis of NiO, Co₃O₄, and CuO nanoparticles from aromatic amine with [M₂(o-tol)₂(H₂O)₈]Cl₄ precursor complex.

EXPERIMENTAL

Chemicals and Instrument Techniques

All the chemicals (NiCl₂ · 6H₂O, CoCl₂ · 6H₂O, CuCl₂ · 2H₂O, and *ortho*-tolidine) and the solvents (methanol) were purchased from Sigma-Aldrich Chemical Company and used without further purification. The FT-IR spectra were recorded in the range 4000–400 cm⁻¹ on Bruker FTIR Spectrophotometer. The electronic spectra were recorded in the range 200–800 nm at room temperature in the solid-state using a UV2 Unicam UV/Vis Spectrophotometer. Microanalyses (C, H and N) were recorded on a Perkin Elmer 2400 CHN analyzer. Melting points of the compounds were determined in open capillaries in an electrical MPS10-120 melting point apparatus. The magnetic moments were determined on a Guoy balance and the diamagnetic corrections of the complexes were calculated using Pascal's constants. Molar conductivities were measured in DMSO solution at 10⁻³ M concentration using a Jenway 4010 conductivity meter. The metal contents were estimated with a gravimetric method at 800°C by converted the synthesized metal complexes to metal oxides as a stable form that suitable to calculate the percentage of metal ions. The X-ray diffraction patterns were recorded on X'Pert PRO PANalytical X-ray powder diffraction, target copper with secondary monochromate. The transmission electron microscopy images (TEM) were performed using JEOL 100s microscopy.

Synthesis of *ortho*-tolidine precursor complex and nanoparticle oxides

The precursors [M₂(o-tol)₂(H₂O)₈]Cl₄ (where o-tol is *ortho*-tolidine compound, M = Ni²⁺, Co²⁺, Cu²⁺) were synthesized according to the briefly steps as follows, 4.25 grams of *ortho*-tolidine (20 mmol) was dissolved in 20 mL of methanol, and 20 mL of water solution of NiCl₂ · 6H₂O, CoCl₂ · 6H₂O, or CuCl₂ · 2H₂O (20 mmol) was added with heating at 70°C and continuously stirring. The color precipitates of [M₂(o-tol)₂(H₂O)₈]Cl₄ are collected on a paper filter, washed with methanol and ether, and then dried under vacuum over anhydrous calcium chloride. The composition of the complexes was confirmed by elemental analysis, electronic, magnetic, molar conductance, FT-IR, and thermal analyses. Anal. calc. for [Ni₂(o-tol)₂(H₂O)₈]Cl₄: C, 40.62; H, 5.84; N, 6.77; Cl, 17.13; Ni, 14.18; found: C, 40.43; H, 5.82; N, 6.67; Cl, 17.08; Ni, 14.01, yield: 77%. M.p. 325°C. Anal. calc. for [Co₂(o-tol)₂(H₂O)₈]Cl₄: C, 40.60; H, 5.84; N, 6.76; Cl, 17.12; Co, 14.23; found: C, 40.54; H, 5.80; N, 6.72;

Cl, 17.11; Co, 14.12, yield: 73%. M.p. 359°C. Anal. calc. for [Cu₂(o-tol)₂(H₂O)₈]Cl₄: C, 40.15; H, 5.78; N, 6.69; Cl, 16.93; Cu, 15.17; found: C, 40.09; H, 5.70; N, 6.61; Cl, 16.88; Cu, 15.03, yield: 79%. M.p. 368°C.

The NiO, Co₃O₄, and CuO nanoparticles were synthesized by the thermal decomposition of [Ni₂(o-tol)₂(H₂O)₈]Cl₄, [Co₂(o-tol)₂(H₂O)₈]Cl₄, and [Cu₂(o-tol)₂(H₂O)₈]Cl₄ complexes, respectively as a precursor. The resulting metal-complex in solid-state was calcinated at ~600°C for three hours and was then cooled to room temperature (Scheme 1). The color solid powders were washed with methanol at least three times to remove any impurities and dried at 100°C.

Scheme 1. Thermal decomposition route of synthesis NiO, Co₃O₄, and CuO by using [M₂(o-tol)₂(H₂O)₈]Cl₄ precursors

RESULTS AND DISCUSSION

Interpretations of [M₂(o-tol)₂(H₂O)₈]Cl₄ precursors

Analytical and molar conductance data

The [M₂(o-tol)₂(H₂O)₈]Cl₄ complexes of nickel, cobalt, and copper (II) metal ions were prepared by heating together methanol/distilled H₂O solutions of the appropriate ligand and metal chlorides with 1:1 molar ratio. All the prepared complexes are stable at room temperature. The prepared complexes are insoluble in methanol, ethanol, benzene, and acetonitrile, but soluble in DMSO and DMF. The analytical data (carbon, hydrogen, nitrogen, chloride, and metal ions percentages) are presented as mentioned in the experimental section. The molar conductance values of the complexes of (10⁻³ M solution in DMSO) are found to be in the range of 180–225 ohm⁻¹ cm² mol⁻¹. These high values indicate that the complexes are ionic with an electrolytic nature¹⁵.

Infrared spectra

By comparison between the spectra of both nickel, cobalt, copper(II) complexes (Fig. 1) and the data of o-tol ligand have been studied and assigned in Table 1. In the case of o-tol free ligand, the distinguish stretching vibration bands of $\nu(\text{N-H})$ of NH_2 group and some of stretching vibrations of $\nu(\text{C-H})$ aromatic rings are exhibited at 3475, 3412, 3375, 3338, 3213, 3019 cm^{-1} ³¹. It is found that the frequencies of $-\text{NH}_2$ groups are shifted to a lower wavenumber at the range 3466–3337 cm^{-1} , which indicates that the interactions placed among the nitrogen of $-\text{NH}_2$. To place greater emphasis on the interactions between the metal ions and o-tol ligand, the 2000–1000 cm^{-1} region was investigated. This region contains the bending vibration motions of $-\text{NH}_2$ group δNH_2 which is influenced by complexation and shifted to lower wavenumbers and consequently, the intensity was distorted. Peaks above 3400 cm^{-1} in the Co(II), Ni(II) and Cu(II) complexes, indicated the presence of coordinated water³¹. The confirming coordination evidence is also displayed by the presence of new bands in the spectra of all the complexes that occur in the range of 585–508 cm^{-1} and 443–404 cm^{-1} are the characteristic bands of stretching vibrations $\nu(\text{M-O})$ and $\nu(\text{M-N})$ respectively³¹ that are disappeared in the free ligand spectrum.

UV-Vis spectra and magnetic susceptibility

The electronic spectrum of copper(II) o-tol complex has three electronic absorption bands at 12422, 17007 and 20747 cm^{-1} due to ${}^2\text{B}_{1g} \rightarrow {}^2\text{B}_{2g}$, ${}^2\text{B}_{1g} \rightarrow {}^2\text{A}_{2g}$ and ${}^2\text{B}_{1g} \rightarrow {}^2\text{E}_{1g}$ transitions respectively, which confirmed that Cu(II) complex has a distorted octahedral geometry³². The electronic spectrum of the cobalt(II) complex has three absorption bands at 10965 cm^{-1} , 17544 cm^{-1} and 21505 cm^{-1}

assigned to ${}^4\text{T}_{1g}(\text{F}) \rightarrow {}^4\text{T}_{2g}(\text{F})$, ${}^4\text{T}_{1g}(\text{F}) \rightarrow {}^4\text{A}_{2g}(\text{F})$ and ${}^4\text{T}_{1g}(\text{F}) \rightarrow {}^4\text{T}_{2g}(\text{P})$ electronic transitions respectively, due to octahedral geometry structure³³. The absorption spectrum of nickel(II) complex included a three electronic bands at 27397 cm^{-1} , 16287 cm^{-1} , and 10288 cm^{-1} assigned to ${}^3\text{A}_{2g}(\text{F}) \rightarrow {}^3\text{T}_{2g}(\text{F})$, ${}^3\text{A}_{2g}(\text{F}) \rightarrow {}^3\text{T}_{1g}(\text{F})$, and ${}^3\text{A}_{2g}(\text{F}) \rightarrow {}^3\text{T}_{2g}(\text{P})$ transitions respectively, these transitions agreement with octahedral geometry. The magnetic moment of the copper(II) complex (1.81 BM) is matched with the octahedral geometry. The magnetic moment value for the nickel (II) complex is 3.10 BM due to the octahedral environment around Ni(II) metal ion. Besides this, the magnetic moment of the cobalt (II) complex is 4.64 BM which consistent with octahedral geometry³³.

Interpretations of prepared nickel, cobalt, and copper oxides

Nickel, cobalt, and copper oxides nanoparticles have been synthesized *via* thermal decomposition of a new precursor $[\text{M}_2(\text{o-tol})_2(\text{H}_2\text{O})_8]\text{Cl}_4$ ($\text{M} = \text{Cu}^{2+}$, Co^{2+} , Ni^{2+}) at $\sim 600^\circ\text{C}$. The products were characterized by FT-IR, XRD, and TEM.

Characterizations of NiO oxide

Figure 2 illustrated the X-ray diffraction patterns for the NiO nanoparticles. Two very sharp significant diffraction peaks were detected at $2\theta = 37.3^\circ$, and 44.4° assigned to (111) and (200) crystalline planes. The XRD spectrum indicates the face-centered cubic lattice structure with a high degree of crystallinity concerning the prepared NiO NPs. The average crystallite size (D) of NiO is estimated based on Debye–Scherrer formulas³⁴, $D = k\lambda / \beta \cos\theta$, where β = FWHM (full width at half maximum), θ is the diffraction angle corresponding to maximum intensity peak in XRD pattern (200), k is an

Table 1. Infrared frequencies/ cm^{-1} and tentative assignments of o-tol and its complexes

O-tol	Ni(II) complex	Co(II) complex	Cu(II) complex	Assignments
3475 3412 3375 3338	3357	3551 3466 3408 3370 3337	3448 3353	$\nu(\text{O-H})$; H_2O $\nu(\text{N-H})$; NH_2
3213 3019	3210	3239 3013	3220 3019	$\nu(\text{C-H})$; aromatic rings
2982 2940 2898 2856	2980	2976 2930 2855	2916 2855	$\nu_s(\text{C-H})$; CH_3 $\nu_{as}(\text{C-H})$; CH_3
1870 1625 1574 1520 1489	1620 1489	1621 1488	1620 1511 1482	Overtone of $\delta(\text{CH})$ $\nu(\text{C=C})$ $\delta(\text{NH}_2)$ Ring breathing bands
1458 1384 1321 1295 1269 1154 1065 1039	1382 1272 1243 1202 1161 1094 1027	1450 1378 1312 1261 1194 1148 1054	1421 1379 1312 1158 1042	$\delta_{as}(\text{CH}_3) + \delta_s(\text{CH}_3)$ $\nu(\text{C-C}) + \nu(\text{C-N})$ In-plane bending
986 944 902 887 855 829 777 735	866 803 755	985 941 881 823 734	993 941 876 814	(C-H) bend Aromatic rings vibrations
682 661 609 583 525 425	717	682 653 607	671 636 589	Aromatic rings vibrations of ortho substituted Skeletal vibrations
–	585 522	574 519	508	$\nu(\text{M-O})$
–	443 404	442	436	$\nu(\text{M-N})$

Figure 1. FT IR spectra of a-Cu(II), b-Co(II), and c-Ni(II) o-tol complexes

empirical constant equal to 0.9. Figure 3a reveals the size, shape, and morphology of the prepared NiO NPs checked by TEM image. The average crystallite size is found to be 9–12 nm, moreover, the figure confirms the spherical shape of NiO NPs with slight agglomeration. The spherical shape offers a good contact area, which is recommended for biosensing applications³⁵. The crystallinity index (I_{crys}) assigns the mono-crystallinity or poly-crystallinity of the nanoparticles if its value is ap-

Figure 2. XRD diffraction patterns of NiO, Co_3O_4 , and CuO oxides

proaching or exceeding one, respectively. It is evaluated using the following equation³⁶: $I_{\text{crys}} = D(\text{TEM})D(\text{XRD})$. The crystallinity index is equal to 0.34, suggesting the mono-crystallinity of NiO nanoparticles. Figure 4 represents the FT IR spectrum of the prepared NiO NPs. The spectrum demonstrates a significant peak at 466 cm^{-1} which is related to the vibrational mode of Ni-O bond. The weak broad peaks occur at $\sim 1630\text{ cm}^{-1}$ and 3400 cm^{-1} are assigned to H-O-H bending vibrations mode and O-H stretching vibrations bond of crystalline water molecules as moisture on the surface of the prepared NiO oxide respectively³¹. Elemental analysis was performed to evaluate the elemental composition of the NiO NPs using EDX spectroscopy. The EDX spectrum of the NiO NPs exhibits distinguish peaks corresponding to Ni and O, as shown in Figure 5.

Characterizations of Co_3O_4 oxide

The XRD pattern of the prepared Co_3O_4 in Figure 2, exhibits some diffraction peaks with 2θ values at 18.91° , 31.27° , 36.75° , 38.43° , 44.76° , 55.57° , and 59.22° . These diffraction peaks can be indexed to the crystalline cubic phase Co_3O_4 with a space group of $\text{Fd}\bar{3}\text{m}$, which agrees with the reported values (JCPDS Card No. 76–1802)³⁷. This result confirms that the Co_3O_4 phase started to appear at 600°C , as indicated by the FT-IR result (Figure 4). No impurity diffraction peaks were detected in the patterns, indicating that the product is of high purity. Furthermore, the diffraction peaks are markedly sharpness due to the small size effect of the particles. The average sizes of the Co_3O_4 particles were calculated

Figure 3. TEM images of a-NiO, b- Co_3O_4 , and c-CuO oxides

Figure 4. FT IR spectra of NiO, Co_3O_4 , and CuO oxides

by the Debye–Scherrer equation³⁴. The average size of the Co_3O_4 nanoparticles calculated using the most intense peak (311) at $2\theta = 36.75^\circ$ is approximately 12 nm. The TEM image and size distribution of the prepared Co_3O_4 NPs are shown in Figure 3. It can be seen from this Figure, that the nanoparticles show approximately black spots spherical morphologies with a uniform size. It is also can find from this figure that the morphology of the particles is almost homogeneous. The diameter sizes of the prepared Co_3O_4 NPs are approximately in the range of 8 to 10 nm with a narrow size distribution. The average particle size is 10 nm, which agrees with the result calculated for the half-width of diffraction peaks using the Scherrer's formula, allowing for experimental error. The FT-IR spectrum of the prepared Co_3O_4 has two strong bands of the spinel-type Co_3O_4 structure at about 672 and 590 cm^{-1} are observed. The former band is characteristic of Co^{3+} –O vibration in an octahedral site, and the latter one is attributable to the Co^{2+} –O vibration in a tetrahedral site of the Co_3O_4 lattice^{37, 38}. The chemical purity and stoichiometry of the product were also examined by EDX analysis. Figure 5 shows the EDX spectrum of the Co_3O_4 nanoparticles prepared by the decomposition of $[\text{Co}_2(\text{o-tol})_2(\text{H}_2\text{O})_8]\text{Cl}_4$ at 600°C. Only oxygen and cobalt elements existed in the product. The atomic percentages of Co and O were found to be 71.02% and 28.98%, respectively. The carbon peak at about 0.277 keV corresponds to the TEM holding grid. No other elements can be detected, indicating the high purity of the Co_3O_4 nanoparticles.

Characterizations of CuO oxide

For XRD patterns of the CuO nanoparticles, all peaks can be confirmed to be the monoclinic phase of CuO (JCPDS no. 48–1548)³⁵ as shown in Figure 2. The smaller size of CuO nanoparticles can be predicted consistently with the broadening diffraction peaks of XRD patterns. Moreover, the crystallite size based on the broadening diffraction peaks was approximately estimated from the corresponding X-ray spectral peak employing the Debye-Scherrer's formula³⁴. The calculated value was estimated to be 15 nm. Figure 3c showed the morphology of highly crystalline CuO nanoparticles from TEM analysis. Nevertheless, the accurate sizes and morphology of the nanoparticles can be estimated from the TEM analysis, TEM images can reveal the internal structure and more accurate measurement of particle size (9–15 nm) and morphology. FTIR spectrum revealed vibration of the CuO band at 524 cm^{-1} (Fig. 4). The corresponding EDX (Fig. 5) spectrum can also confirm the presence of Cu and O elements in the sample. The spherical CuO nanoparticles are evaluated by EDX quantitative analysis software (Oxford Instrument) and found to have 55.62

at% of Cu and 44.38 at% of O. If it is in atomic %, theoretically the Cu will be 50% and O will be 50%. But in the experimental found 55.62 at% of Cu and 44.38 at% of O. Because of the EDX, analysis techniques can select only one area. Thus, the amount of Cu and O in a different area may be different values, so in the dispersion of CuO nanoparticles were found into a high and poor dispersion, respectively.

ACKNOWLEDGMENT

Taif University Researches Supporting Project number (TURSP-2020/01), Taif University, Taif, Saudi Arabia.

LITERATURE CITED

1. Noller, C.R. (1960). *Textbook of Organic Chemistry*, Springer Verlag.
2. Hunger, K. & Herbst, W. (2012). "Pigments, Organic" in *Ullmann's Encyclopedia of Industrial Chemistry*, Wiley-VCH, Weinheim, DOI: 10.1002/14356007.a20_371.
3. Ahangaran, F. & Navarchian, A.H. (2020). Recent advances in chemical surface modification of metal oxide nanoparticles with silane coupling agents: A review. *Adv. Colloid. Interface Sci.* 286. 102298. DOI: 10.1016/j.cis.2020.102298.
4. Rahal, H.T., Awad, R., Abdel Gaber, A.M. & Bakeer, D. (2017). Synthesis, characterization, and magnetic properties of pure and EDTA-capped NiO nanosized particles. *J. Nanomaterials*, 2017, 9. DOI: 10.1155/2017/7460323.
5. Al Boukhari, J., Zeidan, L., Khalaf, A. & Awad, R. (2019). Synthesis, characterization, optical and magnetic properties of pure and Mn, Fe and Zn doped NiO nanoparticles. *J. Chem. Phys.*, 516, 116–124. DOI:10.1016/j.chemphys.2018.07.046.
6. Meng, F., Shi, W., Sun, Y., Zhu, X., Wu, G., Ruan, C., Liu, X. & Ge, D. (2013). Nonenzymatic biosensor based on CuO nanoparticles deposited on polypyrrole nanowires for improving detection range. *J. Biosens. Bioelectr.* 42, 141–147. DOI: 10.1016/j.bios.2012.10.051.
7. Gao, Q., Zeng, W. & Miao, R. (2016). Synthesis of multifarious hierarchical flower-like NiO and their gas-sensing properties. *J. Mat. Sci. Mat. Electron.*, 27(9), 9410–9416. DOI: 10.1007/s10854-016-4986-3.
8. Koh, I. & Josephson, L. (2009). Magnetic nanoparticle sensors. *J. Sensors*, 9(10), 8130–8145. DOI:10.3390/s91008130.
9. Nur, S., Yazid, A.M., Md Isa, I., Abu Bakar, S., Hashim, N. & Ab Ghani, S. (2014). A review of glucose biosensors based on graphene/metal oxide nanomaterials. *Analyt. Lett.*, 47(11), 1821–1834. DOI: 10.1080/00032719.2014.888731.
10. Wu, R., Wu, J., Yu, M., Tsai, T. & Yeh, C. (2008). Applications of Semiconducting Metal Oxides Gas Sensors. *Sens. Actu. B: Chem.*, 131, 306–312. DOI: 10.1016/j.snb.2007.11.033.
11. Mate, V.R., Shirai, M., & Rode, C.V. (2013). Heterogeneous Co₃O₄ catalyst for selective oxidation of aqueous veratryl alcohol using molecular oxygen. *Catal. Commun.*, 33, 66–69. DOI: 10.1016/j.catcom.2012.12.015.
12. Maruyama, T., & Arai, S. (1996). Electrochromic properties of cobalt oxide thin films prepared by chemical vapor deposition. *J. Electrochem. Soc.*, 143, 1383–1386. DOI: 10.1149/1.1836646.
13. Li, Y.G., Tan, B. & Wu, Y.Y. (2008). Mesoporous Co₃O₄ Nanowire Arrays for Lithium Ion Batteries with High Capacity and Rate Capability. *Nano Lett.*, 8, 265–270. DOI: 10.1021/nl0725906.
14. Wang, R.M., Liu, C.M., Zhang, H.Z., Chen, C.P., Guo, L., Xu, H.B. & Yang, S.H. (2004). Porous nanotubes of Co₃O₄: Synthesis, characterization, and magnetic properties. *Appl. Phys. Lett.*, 85, 2080–2082. DOI: 10.1063/1.1789577.

Figure 5. EDX spectra of NiO, Co₃O₄, and CuO oxides

15. Lou, X., Han, J., Chu, W., Wang, X. & Cheng, Q. (2007). Synthesis and photocatalytic property of Co_3O_4 nanorods. *Mater. Sci. Eng., B*, 137, 268–271. DOI: 10.1016/j.mseb.2006.12.002.
16. Warang, T., Patel, N., Santini, A., Bazzanella, N., Kale, A. & Miotello, A. (2012). Pulsed laser deposition of Co_3O_4 nanoparticles assembled coating: Role of substrate temperature to tailor disordered to crystalline phase and related photocatalytic activity in degradation of methylene blue. *Appl. Catal. A: Gen.* 423–424, 21–27. DOI: 10.1016/j.apcata.2012.02.037.
17. Sun, H., Ahmad, M. & Zhu, J. (2013). Morphology-controlled synthesis of Co_3O_4 porous nanostructures for the application as lithium-ion battery electrode. *Electrochim. Acta*, 89, 199–205. DOI: 10.1016/j.electacta.2012.10.116.
18. Lester, E., Aksomaitye, G., Li, J. & Gomez, S. (2012). Controlled continuous hydrothermal synthesis of cobalt oxide (Co_3O_4) nanoparticles. *Prog. Cryst. Growth Charact. Mater.* 58, 3–13. DOI: 10.1016/j.pcrysgrow.2011.10.008.
19. Gardey-Merin, M.C., Palermo, O.M., Belda, R., Fernández de Rapp, M.E., E.Lascalea, G. & Vázquez, P.G. (2012). Combustion synthesis of Co_3O_4 nanoparticles: fuel ratio effect on the physical properties of the resulting powders. *Proced. Mater. Sci.*, 1, 588–593. DOI: 10.1016/j.mspro.2012.06.079.
20. Bhatt, A.S., Bhat, D.K., Tai, C.W. & Santosh, M.S. (2011). Microwave-assisted synthesis and magnetic studies of cobalt oxide nanoparticles. *Mater. Chem. Phys.*, 125, 347–350. DOI: 10.1016/j.matchemphys.2010.11.003.
21. Baydi, M.E., Poillerat, G., Rehspringer, J.L., Gautier, J.L., Koenig, J.F. & Chartier, P. (1994). A sol-gel route for the preparation of Co_3O_4 catalyst for oxygen electrocatalysis in alkaline medium. *J. Solid State Chem.*, 109, 281–288. DOI: 10.1006/jssc.1994.1105.
22. Kim, D.Y., Ju, S.H., Koo, H.Y., Hong, S.K. & Kang, Y.C. (2006). Synthesis of nanosized Co_3O_4 particles by spray pyrolysis. *J. Alloys Compd.*, 417, 254–258. DOI: 10.1016/j.jallcom.2005.09.013.
23. Kumar, R.V., Diamant, Y. & Gedanken, A. (2000). Sonochemical synthesis and characterization of nanometer-size transition metal oxides from metal acetates. *Chem. Mater.*, 12, 2301–2305. DOI: 10.1021/cm000166z.
24. Sinko, K., Szabo, G. & Zrinyi, M. (2011). Liquid-phase synthesis of cobalt oxide nanoparticles. *J. Nanosci. Nanotechnol.*, 11, 1–9. DOI: 10.1166/jnn.2011.3875.
25. Zou, D., Xu, C., Luo, H., Wang, L. & Ying, T. (2008). Synthesis of Co_3O_4 nanoparticles via an ionic liquid-assisted methodology at room temperature. *Mater. Lett.*, 62, 1976–1978. DOI: 10.1016/j.matlet.2007.10.056.
26. Jiang, J. & Li, L. (2007). Synthesis of sphere-like Co_3O_4 nanocrystals via a simple polyol route. *Mater. Lett.*, 6, 4894–4896. DOI: 10.1016/j.matlet.2007.03.067.
27. Fan, S., Liu, X., Li, Y., Yan, E., Wang, C., Liu, J. & Zhang, Y. (2013). Non-aqueous synthesis of crystalline Co_3O_4 nanoparticles for lithium-ion batteries. *Mater. Lett.*, 91, 291–293. DOI: 10.1016/j.matlet.2012.10.008.
28. Masoomi, M.Y. & Morsali, A. (2012). Applications of metal–organic coordination polymers as precursors for preparation of nano-materials. *Coord. Chem. Rev.*, 256, 2921–2943. DOI: 10.1016/j.ccr.2012.05.032.
29. El-Trass, A., Elshamy, H., El-Mehasseb, I. & El-Kemary, M. (2012). CuO nanoparticles: synthesis, characterization, optical properties and interaction with amino acids. *Appl. Sur. Sci.*, 258(7), 2997–3001. DOI: 10.1016/j.apsusc.2011.11.025.
30. Refat, M.S. (2007). Complexes of uranyl(II), vanadyl(II) and zirconyl(II) with orotic acid “vitamin B13”: Synthesis, spectroscopic, thermal studies and antibacterial activity. *J. Mol. Struct.*, 842(1–3), 24–37. DOI: 10.1016/j.molstruc.2006.12.006.
31. Nakamoto, K. (1997). Infrared and Raman Spectra of Inorganic and Coordination Compounds, Wiley, New York.
32. Lever, A.B.P. & Mantovani, E. (1971). Far-infrared and electronic spectra of some bis(ethylenediamine) and related complexes of copper(II) and the relevance of these data to tetragonal distortion and bond strengths. *Inorg. Chem.*, 10, 817–826. DOI: 10.1021/ic50098a031.
33. Lever, A.B.P. (1968). Inorganic Electronic Spectroscopy, Elsevier, Amsterdam, (1968).
34. Waseda, Y., Matsubara, E. & Shinoda, K. (2011). X-Ray Diffraction Crystallography. Verlag, Berlin Heidelberg: Springer. DOI: 10.1007/978-3-642-16635-8.
35. Kolhatkar, A., Jamison, A., Litvinov, D., Willson, R. & Lee, T. (2013). Tuning the magnetic properties of nanoparticles. *Int. J. Mol. Sci.*, 14(8), 15977–16009. DOI:10.3390/ijms140815977.
36. Rifaya, M.N., Theivasanthi, T. & Alagar, M. (2012). Chemical capping synthesis of nickel oxide nanoparticles and their characterizations studies. *Nanosci. Nanotechnol.*, 2(2), 134–138. DOI: 10.5923/j.nn.20120205.01.
37. Farhadi, S., Javanmard, M. & Nadri, G. (2016). Characterization of cobalt oxide nanoparticles prepared by the thermal decomposition. *Acta Chim. Slov.*, 63, 335–343. DOI: 10.17344/acs.2016.2305.
38. Tamaekong, N., Liewhiran, C. & Phanichphant, S. (2014). Synthesis of thermally spherical CuO nanoparticles. *J. Nanomaterials*, 2014, Article ID 507978, 5 pages. DOI: 10.1155/2014/507978.